



Notes:

1. When radiography is used for testing, no tack welds shall be in test area.
2. The backing thickness shall be 1/4" in min to 3/8" max. backing width shall be 3" min when not removed for radiography, otherwise 1" min.